



Scotch® Super 88™

Vinyl Electrical Tape

1. Product Description

Scotch® Vinyl Electrical Tape Super 88 is a premium grade, 0,22 mm thick, all-weather vinyl insulating tape. It is designed to perform continuously in ambient temperatures up to 105 °C. The tape is conformable for cold weather applications down to -18 °C. It has high resistance to abrasion, moisture, alkalis, acids, corrosion and varying weather conditions.

The combination of elastic backing and aggressive adhesive provides moisture-tight electrical and mechanical protection with minimum bulk. Scotch® Tape Super 88 is UL Listed, CSA approved and has a VDE Marks License for IEC 60454-3-1-7/F-PVC P/90.

- Polyvinyl chloride (PVC) backing
- Pressure-sensitive rubber-based adhesive
- Compatible with solid dielectric cable insulations
- Compatible with rubber and synthetic splicing compounds, as well as epoxy and polyurethane resins
- Inhibits corrosion of electrical conductors
- For indoor or outdoor applications

2. Applications

- Primary electrical insulation for all wire and cable splices rated up to 600 Volts and up to 105 °C
- Primary electrical insulation for 600-Volt bus applications, and protective jacketing for low- and high-voltage bus
- Protective jacketing for high-voltage cable splices and repairs
- Harnessing of wires and cables

3. Typical Properties

| Physical Properties | Typical Value |
|---|------------------------------|
| Temperature Rating - UL 510 | 80 °C |
| Temperature Rating Continuous Operating Temperature (IEC60454-3-1) max. Temperature (CSA C22.2) | -18 °C up to 90 °C 105 °C |
| Colour | Black |
| Thickness | 0,22 mm |
| Adhesion to Steel (ASTM D1000) 22 °C -18 °C | 3,0 N/10 mm 6,5 N/10 mm |
| Adhesion to Backing (ASTM D1000) 22 °C -18 °C | 3,0 N/10 mm 6,5 N/10 mm |
| Breaking Strength (ASTM D1000) 22 °C | 35 N/10 mm |
| Ultimate Elongation (ASTM D1000) 22 °C -18 °C | 250% 100% |
| Flammability (Maximum) UL 510 ASTM D-1000 | 1 sec. 4 sec. |
| Flagging (ASTM D1000) | <2,5 mm |
| Telescoping 24 Hours W 50 °C | <2,5 mm |
| Electrical Properties | Typical Value |
| Voltage Rating (UL510) | 600 Volts |
| Dielectric Breakdown Standard Condition V/mm High Humidity | 10 kV 90% of standard |
| Insulation Resistance (High Humidity Method) | >1x10 ⁶ Megohms |

Properties measured at room temperature 23 °C unless otherwise stated.

4. User Information

4.1 Specifications

Scotch® Vinyl Electrical Tape Super 88 is based on polyvinyl chloride (PVC) and/or its copolymers, and has a rubber-based, pressure-sensitive adhesive. The tape is 0,22 mm thick, UL Listed and marked per UL Standard 510 as “Flame-Retardant and Cold Resistant.” The tape can be applied at temperatures ranging from -18 °C through 38 °C, without loss of physical properties and is compatible with synthetic cable insulations, jackets and splicing compounds. Scotch® Tape Super 88 will remain stable and will not telescope more than 2,54 mm when maintained at temperatures below 50 °C.

4.2 Engineering/Architectural Specification

Primary electrical insulation (branch wiring in wet or dry locations): All splices 600-Volt wire rated 105 °C and below should be insulated with a minimum of two half-lapped layers of Scotch® Vinyl Electrical Tape Super 88. All connectors having irregular surfaces should be padded with 3M™ Scotchfil™ Electrical Insulation Putty or Scotch® Linerless Rubber Splicing Tape 130C prior to insulating with this tape.

Mechanical Protection (outer jacketing)

All rubber and thermoplastic insulating high voltage power cable tape splices and repairs should be over wrapped with at least two half-lapped layers of Scotch® Tape Super 88.

4.3 Installation Techniques

Scotch® Tape Super 88 should be applied in half-lapped layers with sufficient tension to produce a uniform wind (for most applications this tension will reduce the tape’s width to approximately 60% of its original width). On pigtail splices, the tape must be wrapped beyond the end of the wires and then folded back, leaving a protective cushion to resist cut-through. Wrap tape up-hill, taping from a smaller diameter surface to a larger diameter surface. Apply the tape with no tension on the last wrap to prevent flagging.

4.4 Agency Approvals & Self Certifications

- UL Listed; UL 510 Standard “Insulating Tape” (product category OANZ), File E129200
- CSA Certification; Standard C22.2 No.197-M1983 “PVC Insulating Tape,” File LR 48769
- VDE Marks License no. 130462 for Type 7: IEC 60454-3-1-7/F-PVC P90
- For RoHS information, please visit www.3M.com/RoHS

4.5 Shelf Life & Storage

This product has a 5-year shelf life from date of manufacture when stored in a humidity controlled area (10 °C to 27 °C and <75 % relative humidity).

3M Deutschland GmbH
Carl-Schurz-Str.1
41453 Neuss
Germany

Reference: AABCC04061_02
© 3M 2020 All Rights Reserved.

Issue date 21.01.2020
Supersedes July 2011

4.6 Availability

Please contact your local distributor

5. Additional Information

To request additional product information, see address below.

Important Notice

All statements, technical information and recommendations contained in this document are based upon tests or experience that 3M believes are reliable. However, many factors beyond 3M's control can affect the use and performance of a 3M product in a particular application, including the conditions under which the product is used and the time and environmental conditions in which the product is expected to perform. Since these factors are uniquely within the user's knowledge and control, it is essential that the user evaluates the 3M product to determine whether it is fit for a particular purpose and suitable for the user's method or application.

Values presented have been determined by standard test methods and are average values not meant to be used for specification purposes.

All questions of warranty and liability relating to 3M products are governed by the terms of the respective sale subject, where applicable, to the prevailing law.

3M is a trademark of the 3M Company.

3M Deutschland GmbH
Carl-Schurz-Str.1
41453 Neuss
Germany

Reference: AABCC04061_02
© 3M 2020 All Rights Reserved.

Issue date 21.01.2020
Supersedes July 2011